


Silitec Fibers SILIRANGE Single-Mode Optical Fiber ITU-T G.652.D



PRODUCT INFORMATION

The Silitec Fibers SILIRANGE G.652.D single-mode fiber is the optimal solution for most applications, ranging from long-haul to LAN, through regional and metropolitan networks, as well as for the specific requirements of cable TV, utilities, ISP's and private networks. The fiber has a very low PMD coefficient, making it suitable for future network upgrades to higher data rates.



ISO 9001 : 2000 / ISO 14001 : 2004

Silitec Fibers SILIRANGE Single-Mode Optical Fiber ITU-T G.652.D

OPTICAL SPECIFICATIONS & CHARACTERISTICS

Attenuation

At 1310 nm	≤ 0.34 dB/km
at 1383 nm (after H2 aging)	≤ 0.34 dB/km
at 1550 nm	≤ 0.21 dB/km
at 1625 nm	≤ 0.23 dB/km

Point Discontinuities

at 1550 nm	≤ 0.05 dB
at 1625 nm	≤ 0.05 dB

Attenuation Uniformity

at 1550 nm	≤ 0.05 dB/km
------------	--------------

Bending Loss

Radius	Nb of turns	Wavelength	Induced Attenuation
16 mm	1	1550 nm	≤ 0.5 dB
25 mm	100	1310 nm	≤ 0.05 dB
25 mm	100	1550 nm	≤ 0.1 dB
30 mm	100	1550 nm	≤ 0.05 dB
30 mm	100	1625 nm	≤ 0.05 dB

Opto-Geometrical Specifications

Mode Field Diameter at 1310nm	9.2 ± 0.4 μm
Mode Field Diameter at 1550nm	10.4 ± 0.5 μm
Cut-Off Wavelength	≤ 1340 nm

Chromatic Dispersion

Wavelength	Minimum	Maximum
Zero dispersion wavelength	1302 nm	1324 nm
at 1550 nm	-	18 ps/(nm.km)
at 1625 nm	-	22 ps/(nm.km)

Polarization Mode Dispersion (PMD)

PMD Link Design Value	≤ 0.03 ps/km ^{1/2}
Individual Fiber (1310-1550nm)	≤ 0.08 ps/km ^{1/2}

Rayleigh Backscattering Coefficient

at 1310 nm	< -77 dB
at 1550 nm	< -82 dB

Group Refractive Index

at 1550 nm	1.470 (typ.)
at 1625 nm	1.471 (typ.)

PHYSICAL CHARACTERISTICS

Glass Geometry

Cladding Diameter	125.0 ± 0.7 μm
Cladding Non-Circularity	≤ 0.7 %
Core-Clad Concentricity Error	≤ 0.5 μm
Fiber Curl	> 4 m

Coating Geometry

Coating Diameter	245 ± 5 μm
Coating Non-Circularity	≤ 5 %
Coating-Cladding Concentricity Error	≤ 12 μm

MECHANICAL SPECIFICATIONS

Proof Test Level	≥ 100 kpsi
Dynamic tensile Strength	≥ 4 GPa
Coating Strip Force	≤ 2 N
Dynamic Fatigue Parameter	n ≥ 20

ENVIRONMENTAL SPECIFICATIONS

Attenuation

Temperature Dependence (-60°C to +85°C)	≤ 0.05 dB/km
Temperature-Humidity Cycling (-10°C to +85°C, 08%rh)	≤ 0.05 dB/km
Water Immersion (40 days at 23±2°C)	≤ 0.05 dB/km
Dry Heat Aging (85°C)	≤ 0.05 dB/km

Coating Strip Force Stability

After 40 days at ambient	≤ 2 N (no change)
After 40 days in water	≤ 2 N (no change)
After 6 thermal cycles (-25°C to +70°C)	≤ 2 N (no change)

Dynamic Tensile Strength Stability

After 3 months in water at 70°C	Max change ≤ 23% (Recommended loss in strength < 25%)
---------------------------------	----------------------------------------------------------